



**SB 300 FM  
#50311**

Typical Physical Properties

Property	Unit of Measure	Typical Value	Test Method
Weight	osy	2.75	ASTM D3776-96 (Opt. C)
Elongation	%	MD 16.4	ASTM D5034-95
		CD 83.6	
Tensile	lbf	MD 55.9	ASTM D5034-95
		CD 48.4	
Trap Tear Strength	lbf	MD 13.2	ASTM D5587-03
		CD 15.1	
Mullen Burst	lbs/sq in	109.7	ASTM D3786-01

Reviewed  
12-20-2017

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent. This information reflects typical properties and should not be considered as specifications.