

# #406 Standard Fibrated Aluminum Roof Coating



The Right Choice for Low-Slope Roofing Products

800-786-1492 • mulehide.com

Rugged • Time Tested • Weather Tested

## Product Description

Mule-Hide #406 Standard Fibrated Aluminum Roof Coating provides high-performance protection for asphalt-based roofing systems, extending their service lives by shielding them from damaging heat, ultraviolet light, mold, fungus and rust. The heavy-bodied coating delivers excellent reflectivity.

- Designed for application to new or existing APP or SBS modified bitumen cap sheets (smooth and granulated), asphalt built-up roofs, and flashings.
- Can be used to coat a variety of other substrates, including masonry surfaces, and structural steel.
- Should only be applied to areas with positive drainage.
- **Product must be mixed very well with a power drill until coating appears silver. Hand mixing is not satisfactory. Average mix time per bucket should be approximately 2 minutes.**

## Features & Benefits

- Bright silver finish
- Contains aluminum paste to protect the roof from rust, fungus, and mold.
- Forms a strong bond with the base material.
- Offers excellent weathering characteristics and will not prematurely crack or dry out.
- Does not damage conventional asphalt-based roofing membranes



Packaging: 4.7 Gallon Pail,  
50 Gallon Drum

## Application Methods:



## Code Approvals/Compliance:



D2824 Type III

Fed Spec - TCC 1079

## Physical Property Information

Property	Value
Maximum VOC	500 G/L
Consistency	Semi Mastic
Weight	7.8 +/- 0.3 lbs. per gallon
Flash Point (T.C.C)	105°F+
Dry Film Characteristics	Firm, Non-Tacky
Appearance	Bright Aluminum
Drying Time	1-2 hours to touch (average)

# #406 Standard Fibrated Aluminum Roof Coating

Used as a component within these systems:

Mod Bit

M&R

## Frequently Asked Questions

### 1. When should Mule-Hide #406 Standard Fibrated Aluminum Roof Coating be used vs. Mule-Hide #401 Premium Fibrated Aluminum Roof Coating? Why?

For contractors seeking a quality, best-value aluminum roof coating, Mule-Hide #406 Standard Fibrated Aluminum Roof Coating offers exceptional performance. The #401 Premium Fibrated Aluminum Roof Coating should be considered when optics and aesthetics are the paramount objective.

### 2. What are the coverage rate and spray tip sizes for Mule-Hide #406 Standard Fibrated Aluminum Roof Coating?

The coverage rate for Mule-Hide #406 Standard Fibrated Aluminum Roof Coating is approximately 1 to 1.5 gallons per 100 sq. ft. The spray requirements are 3,000 psi at 1.5 gallons per minute. Tip size = 0.051 to 0.067, Fan = 6 inches. (All values are approximate and may vary with ambient temperature and job conditions.)

### 3. How is Mule-Hide #406 Standard Fibrated Aluminum Roof Coating applied?

Mule-Hide #406 Standard Fibrated Aluminum Roof Coating can be applied using a high-pressure sprayer, a roller, or a brush. For best results, spray using proper equipment.

### 4. Can Mule-Hide #406 Standard Fibrated Aluminum Roof Coating be applied to single-ply roofing systems?

NO. DO NOT apply Mule-Hide #406 Standard Fibrated Aluminum Roof Coating to PVC, TPO, EPDM or other single-ply roofing membranes.

### 5. What is the shelf life of Mule-Hide #406 Standard Fibrated Aluminum Roof Coating?

With proper storage, the shelf life of Mule-Hide #406 Standard Fibrated Aluminum Roof Coating is 24 months from the date of manufacture.

### 6. At what temperature should Mule-Hide #406 Standard Fibrated Aluminum Roof Coating be stored?

Mule-Hide #406 Standard Fibrated Aluminum Roof Coating should be stored at a temperature of at least 45°F but not above 120°F. It should be stored at room temperature for at least 24 hours prior to use.

### 7. In what weather conditions can Mule-Hide #406 Standard Fibrated Aluminum Roof Coating be applied?

Mule-Hide #406 Standard Fibrated Aluminum Roof Coating should only be applied when the ambient temperature is at least 50°F and rising. Cold weather can result in uneven application and improper curing, and it will cause the product to stiffen, making application more difficult. Do not apply Mule-Hide #406 Standard Fibrated Aluminum Roof Coating if there is a threat of inclement weather within 24 hours of application.



Mule-Hide #406 Standard Fibrated Aluminum Roof Coating being applied with a roller.

The information herein should not be considered all-inclusive and should always be accompanied by a review of the Mule-Hide specifications and guidelines and good application practices.

This information herein is based upon data and knowledge considered to be true and accurate at the time of printing and is provided for the reader's consideration, investigation and verification. No statement made by anyone may supersede this information, except when done in writing by Mule-Hide Products Co., Inc. Mule-Hide Products Co., Inc. does not warrant any results to be obtained. Statements concerning possible use of Mule-Hide products are made without knowledge of your particular roof and such an application may not be fit for your particular purpose. MULE-HIDE DISCLAIMS ALL WARRANTIES, INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, except written warranties attached to Mule-Hide products and written warranties signed by an officer of Mule-Hide.

Visit the Mule-Hide website at [www.mulehide.com](http://www.mulehide.com) prior to any installation for updated technical specifications and details. Mule-Hide is a U.S. registered trademark. All rights reserved. REV 0 9/21