

System Specifications

"The name trusted in roofing since 1906"



100% Silicone Roof Coating System for Concrete Decks

TABLE OF CONTENTS

PART 1	GENERAL	Page
1.1	Scope of Work	1
1.2	Related Sections	1
1.3	References	1
1.4	Submittals	1
1.5	Quality Assurance	1
1.6	Product Delivery, Storage and Handling	2
1.7	Job Conditions	2
1.8	Precautions	2
1.9	Protection of Buildings and Adjacent Areas	3
1.10	Warranties	3
PART 2	PRODUCTS	
2.1	General	4
2.2	Products	4
2.3	Equipment	5
PART 3	EXECUTION	
3.1	Examination	5
3.2	Existing Conditions and Remedies	6
3.3	Surface Preparation	6
3.4	Application	6
3.5	Protection	8
3.6	Clean-Up	8

**PLEASE CONSULT THE MULE-HIDE WEBSITE FOR THE MOST
CURRENT INFORMATION AT WWW.MULEHIDE.COM**



100% Silicone Roof Coating System for Concrete Decks

Part 1 General

Oct 2024

This specification is a guide for coating and restoration of concrete decks utilizing the Mule-Hide 100% Silicone Roof Coating and accessory products.

1.1 Scope of Work

- A. Contractor will provide all labor, equipment and Mule-Hide labeled materials necessary to install a 100% Silicone Roof Coating System.
- B. Mule-Hide's most current Product Data Sheets and installation instructions shall be followed in conjunction with this specification.
- C. Coverage rates indicated in this specification **Do Not** include calculations for waste. When installing liquid products, the contractor must include a waste factor when calculating quantities of material necessary to meet the project requirements.
- D. Contractor is solely responsible to complete all necessary repairs to the existing concrete deck to restore it to a structurally sound, watertight condition prior to installing the 100% Silicone Roof Coating System.

1.2 Related Sections

- A. Related sections may or may not be applicable to this specification.
- B. Section 07 62 00: Sheet Metal Flashing and Trim: Metal flashing and counterflashing installation and requirements.
- C. Section 22 30 00: Plumbing: Roof drains, scuppers, gutters and downspout installation and requirements.

1.3 References

- A. ASTM D6694 Standard Specification for Liquid-Applied Silicone Coating
- B. NRCA Roofing and Waterproofing Manual
- C. Underwriters Laboratories Building Materials Directory
- D. CRRC (Cool Roof Ratings Council)

1.4 Submittals

- A. Submit Product Data Sheets (PDS) confirming physical and performance properties of each product used in the system.
- B. Submit Safety Data Sheets (SDS) for each product used in the system.
- C. Submit a roof survey including roof type, measurements and descriptions of the condition of the seams, penetrations, drains, gutters, known leaks and a moisture scan or test cuts with an indication of moisture content. Photographs of all conditions should be included in the submission.
- D. Submit a sample copy of the requested warranty type.

1.5 Quality Assurance

- A. Manufacturer Qualifications: Mule-Hide Products Co., Inc. shall provide a roofing system that meets or exceeds the criteria listed in this section.
- B. Contractor must be a Mule-Hide Warranty Eligible Contractor approved for the installation of the products utilized in this system specification.
- C. Supplier shall retain batch samples of all coating products used in the system for a minimum of 5 years.
- D. Prior to work commencing, the Mule-Hide Warranty Eligible Contractor shall submit a fully completed Silicone Roof Coating System Warranty Application to the Mule-Hide Technical Department. Included shall be an accurately dimensioned roof drawing plus photos of any unusual flashing details or roof conditions.

System Specifications

100% SILICONE ROOF COATING SYSTEM FOR CONCRETE DECKS

Oct 2024

- E. Contractor shall furnish all insurance, licenses, permits and certifications as required by local authorities and/or the property owner.
- F. Contractor shall ensure that all work performed at the site shall be in accordance with National Roofing Contractors Association (NRCA) Low Slope Roofing Manual recommendations and all other pertinent guidelines issued by the NRCA in reference to other types of construction present at the job site.

1.6 Delivery, Storage and Handling

- A. All products delivered to the job site shall be in their original unopened containers or wrappings and clearly labeled with the manufacturer's name, product identification and date of manufacture.
- B. Store all materials in a dry, clean area protected from the elements and damage. Place all stored materials on pallets and cover with a tarpaulin. Keep out of direct contact with sunlight.
- C. All liquid products and caulks shall be stored at temperatures between 60°F and 80°F. Materials exposed to lower temperatures affect the workability and performance of the product. Products shall be restored to the above temperature prior to use.
- D. All flammable materials shall be stored in a cool, dry area away from open flames and sparks. Follow precautions outlined on containers or supplied by the material manufacturer/supplier.
- E. All materials determined as being damaged (confirmed by Mule-Hide) due to improper storage on the job site are to be replaced with new materials.

1.7 Job Conditions

- A. The roof must be structurally sound, clean, dry and free of areas of ponding water, ice, snow, rain or dew, oils, grease, particulate matter or other debris.
- B. Roof must be inspected for the following existing conditions:
 - 1. Spalled, damaged or loose substrate
 - 2. Peeling and chalking of previous coatings
 - 3. Poorly attached vents or other projections
 - 4. Areas of ponding water – areas of dirt/debris accumulation
 - 5. Broken or improperly flashed pipes
 - 6. Broken or missing drain components
 - 7. Loose or damaged perimeter edge metal
- C. All deficiencies including all sources of leaks must be properly corrected prior to the installation of the new Silicone Roof Coating System.
- D. The contractor shall follow and comply with all safety regulations as recommended by OSHA.
- E. Any unusual or concealed condition discovered during the preparation of the existing roof surface or installation of the Silicone Roof Coating System is to be reported to the owner and Mule-Hide immediately in writing. Work is to be halted until the owner has responded with a solution to the problems.
- F. All local building codes and requirements should be followed where applicable. It is the roofing contractor's sole responsibility to determine and ensure that the roofing system selected complies with all local codes and requirements.
- G. All air intake ventilation equipment should be shut off and all ductwork openings should be temporarily sealed during product application.

1.8 Precautions

- A. Coatings may require mixing immediately prior to application. If mixing is required, mix at low speed to avoid entraining air into the coating. Coatings shall be mixed no more than 1 (one) hour prior to use.
- B. This product cures through absorption of moisture from the air. Avoid entraining air when mixing. Do not mix at high speeds.
- C. Remixing of 100% Silicone Roof Coating is permitted as necessary.
- D. No products with a "Flash Point" below 100°F shall be permitted due to associated fire hazard.
- E. No products with chlorinated "Toxic Exempt" solvents including perchloroethylene, 111 trichloroethane or methylene chloride or isocyanates shall be utilized due to the associated health hazards to workers and building occupants.
- F. No asphalt or vegetable based oils may be used in the production of any product included in this specification.
- G. Materials should be maintained at a minimum temperature of 50°F for 24 hours prior to the application to ensure the optimal application qualities.
- H. Do not apply coating when ambient temperature is within 5°F of the dew point.
- I. Do not apply coatings during or just before rain, inclement weather or on frost covered or wet surfaces.

System Specifications

100% SILICONE ROOF COATING SYSTEM FOR CONCRETE DECKS

Oct 2024

- J. The concrete deck surface must be a minimum of 35°F to ensure that frozen condensation is not present on the roof surface.
- K. The concrete deck surface should not exceed a maximum of 100°F to avoid blisters and pinholes.
- L. Do not apply to concrete decks that may be subject to vapor drive from conditioned spaces below.

1.9 Protection of Buildings and Adjacent Areas

- A. It is the sole responsibility of the installing contractor to protect all surfaces adjacent to the surfaces to be coated including but not limited to, windows, doors, equipment and wall surfaces, either from overspray, brushing or rolling of the coatings being installed.
- B. All roof top air intake equipment should be turned off and all openings should be sealed to prevent any fumes from entering the building.
- C. When spraying, parking lots adjoining the building should be blocked off sufficiently to protect vehicles from wind borne overspray.

1.10 Warranties

Mule-Hide Roof Coating NDL System Warranties (“System Warranties”) are available for commercial projects when approved by Mule-Hide and installed in compliance with Mule-Hide’s published specifications and details. System warranties are only available when applied for and installed by Mule-Hide Warranty Eligible Contractors. System Warranties are not available for residential projects. Mule-Hide defines a residential project as a single-family dwelling.

- A. Roof Coatings Warranty Application forms must be fully completed and submitted to the Mule-Hide Technical Department prior to beginning the project. Issuance of a warranty will be dependent upon completion of the project to the satisfaction of Mule-Hide and payment of any required warranty fees. Mule-Hide reserves the right to decline to issue any warranties for projects completed before the submittal of the proper Warranty Application to Mule-Hide.
- B. Mule-Hide’s Roof Coatings NDL System Warranties for Commercial Buildings
 - a. Mule-Hide offers a 10, 15 or 20-year Roof Coatings NDL System Warranties. The Roof Coatings NDL System Warranty is available through Mule-Hide Warranty Eligible Contractors only for commercial projects. This warranty is not available for residential projects. This warranty covers leaks due to manufacturing defects, premature weathering and the contractor’s workmanship of the installed product. This warranty does not cover leaks due to movement or deterioration of the existing roof surface to which the Silicone Roof Coating System has been applied, leaks caused by other substrate conditions, components not supplied by Mule-Hide and does not cover the appearance, cleanliness, discoloration or staining of the coating for any reason.
 - b. See the Mule-Hide Roof Coatings NDL System Warranty sample for specific terms and conditions. Please contact the Mule-Hide Technical Department for information and requirements regarding the Mule-Hide Roof Coatings System Warranty Program.

System Specifications

100% SILICONE ROOF COATING SYSTEM FOR CONCRETE DECKS

Oct 2024

Mule-Hide Roof Coatings System warranties require the following minimum application rates:

Table 1

Warranty Type	Cleaner	Primer	100% Silicone Roof Coating
10-year	Clean with 115 Cleaner applied with low pressure sprayer then power washed.	When priming, use 1 coat of Multibase SB @ 1.5 gal/100 sf minimum	1 coat @ 1.5 gal/100 sf (24 wet mils, 23 dry mils)
15-year	Clean with 115 Cleaner applied with low pressure sprayer then power washed.	When priming, use 1 coat of Multibase SB @ 1.5 gal/100 sf minimum	1 coat @ 2.0 gal/100 sf (32 wet mils, 31 dry mils)
20-year	Clean with 115 Cleaner applied with low pressure sprayer then power washed.	When priming, use 1 coat of Multibase SB @ 1.5 gal/100 sf minimum	1 coat @ 2.5 gal/100 sf (40 wet mils, 38 dry mils)

Note: Minimum application rates listed do not include thickness of primers or areas where additional coatings and reinforcement are required.

Part 2 Products

2.1 General

- A. The components of the Mule-Hide Silicone Roof Coating System shall be products manufactured or supplied by Mule-Hide Products Co., Inc.
- B. Components other than those supplied or manufactured by Mule-Hide may be submitted for review and acceptance by Mule-Hide's Technical Department. Any product requested for review and acceptance must be submitted prior to the job start. Mule-Hide's acceptance of any other product is based solely on chemical compatibility and published performance data provided by the component manufacturer. Other components may be considered on a job-by-job basis and must be approved in writing by Mule-Hide's Technical Department. Mule-Hide offers no warranty or guarantee for the performance or suitability of any component not supplied or manufactured by Mule-Hide.

2.2 Products

The following Mule-Hide materials must be used to install Mule-Hide Silicone Roof Coating Systems. Mule-Hide will not warrant any application where another manufacturer's product is substituted for a Mule-Hide product. All products listed below are physically and chemically compatible with each other.

- A. **115 Cleaner** – a biodegradable detergent wash suitable for cleaning and preparing metal and aged roof surfaces (including but not limited to smooth BUR, modified bitumen, EPDM, TPO, Hypalon (CSPE) and PVC roof systems).
- B. **A-125 Metal Roof Primer** - a modified acrylic, high solids, zinc rich primer which totally encapsulates existing rust and inhibits the development of new rust. A-125 provides excellent adhesion for subsequent coats on metal surfaces.
- C. **Multibase SB** – a one-component acrylic coating used as primer to improve adhesion and as a stain blocker. The application rate is 1.5 gal/100 sf for smooth surfaces.
- D. **100% Silicone Sealant** – a high solids, moisture-cure silicone sealant intended for sealing joints in masonry, architectural metal, metal roof seams and fasteners and miscellaneous repairs prior to coating.
- E. **100% Silicone Roof Coating** - This product is a 100% silicone based, single-component roof coating that creates a barrier that is resistant to normal weathering, is durable, breathable and weatherproof. This product meets or exceeds the requirements of ASTM D6694. Refer to the Mule-Hide Product Data Sheets for physical properties and additional information.
- F. **JTS-1 Joint & Termination Sealant** - is a fast curing, 100% solids, non-shrink, performance sealant for use in multiple types of construction where significant movement or vibration is expected. Ideal for roof terminations and expansion joints. Sealant has excellent adhesions to concrete, masonry, EPDM, PVC, wood, vinyl and most other common building materials.
- G. **Seal-Fast Liqui-Flash** - is a single component, non-shrink, advanced technology polyurethane sealant designed for filling and sealing pitch pockets and pans, metal roof seams & fasteners, inlaid gutters, polyurethane foam, aged smooth asphalt and modified bitumen and aged PVC and EPDM roofs.
- H. **MP Liquid Sealant** – a single component, non-shrink, polyurethane sealant used for filling/topping pitch pans.

System Specifications

100% SILICONE ROOF COATING SYSTEM FOR CONCRETE DECKS

Oct 2024

- I. **ShapeShift Pitch Pans** – high-strength polymer straight and outside corner sections that snap-lock together to create custom sized pitch pans to seal around various roof penetrations.
- J. **Walkway Granules** – Mule-Hide Walkways granules are colored EPDM granules available in gray or safety yellow used with the 100% Silicone Roof Coating to provide a non-slip surface over a Mule-Hide Silicone Roof Coating System in areas of foot traffic or service areas.
- K. **Tietex® 325 Poly Fabric** – a stitch-bonded polyester product that offers high-strength properties with good elongation for excellent thermal stress force accommodations. Tietex 325 Poly Fabric is a soft polyester that will readily conform to surface irregularities and is easy to handle.

2.3 Equipment

- A. Spray Equipment (optional) – Mule-Hide recommends the Graco GH 933ES Hi-Flo Big Rig sprayer with a Monarch 5:1 pump, 3/4" material hose (7,250 psi) up to 250 ft., 1/2" whip, XHF spray gun (7,250 psi) with a XDF 7,250 psi tip (.029 - .035). The recommended pressure at the gun should be 3,000 psi while spraying (Note: Pump lower must be set to maximum lower-ball travel). Please contact Mule-Hide Technical Department for more detailed information.
Note: Use of the Monarch pump requires the use of an air compressor capable of delivering 20CFM @ 90 psi.
- B. Miscellaneous equipment includes 3/4" to 1-1/4" nap, lint free, 9" roller covers and rollers, 6" handles, 4" double wide chip brushes, roofers' trowels, scissors for cutting fabric and a 1/2" power drill with mixing attachment.
- C. Miscellaneous hand and power tools may be required to complete any repairs to the existing roof.

Part 3 Execution

3.1 Examination

- A. Prior to bidding the project a pre-inspection of the roof should take place with the Warranty Eligible Contractor and a Mule-Hide representative to review the conditions of the roof and determine if the roof is suitable for the application of a Mule-Hide Silicone Roof Coating System.
- B. Adhesion Tests
 1. An adhesion test is required and any Concrete roof systems having an existing coating covering the roof surface shall also be required to have adhesion tests performed While there is no actual ASTM test method for field testing of adhesion for roof coatings, many manufacturers will reference ATSM D903 or ASTM D3359. Mule-Hide follows ASTM D903 and ASTM D6083 with modifications.
 2. When an adhesion test is needed follow the procedure outlined in Mule-Hide Technical Bulletin 1803, Roof Coating Adhesion Test and submit the test results to the Mule-Hide Technical Department for review and comment.
 3. Every adhesion test is required to have a corresponding photo when submitting for a NDL warranty.

3.2 Existing Conditions and Remedies

- A. Prior to the commencement of work, the deck shall be re-inspected and any conditions not included in the roof survey shall be added and noted. All new information must be communicated to the Mule-Hide prior to starting work.
- B. The deck assembly must be structurally sound and free of damaged concrete. Defects and leaks shall be remedied prior to the installation of the Silicone Roof Coating System.
- C. Drains are recommended to be installed to allow positive drainage of the deck surface. Retained water may not cover more than 5% of the deck surface. If it is not possible to install drains, areas of light ponding (must evaporate within 48 hours as defined by the NRCA) may be addressed by use of an approved, compatible cementitious filler/leveling compound prior to application of the Silicone Roof Coating System. Any areas where ponding remains beyond 48 hours shall require an increased rate of at least 1(one) additional gallon per 100 sf.
- D. Existing flashings shall be properly terminated according to NRCA guidelines or the original project specifications. Defective terminations shall be remedied. Damaged flashings shall be repaired prior to installation of the Silicone Roof Coating System.
- E. Curbs and penetrations must not interrupt the flow of water off the roof. If defects are present, install crickets to divert water around the penetrations.
- F. If the existing deck surface has been previously coated, adhesion tests must be performed. See Section 3.1.B. Adhesion Tests.
- G. If the existing deck surface contains aluminum coating, pressure wash the substrate, utilizing the 115 Cleaner as needed, to remove the loose aluminum flakes from the substrate. A change in color from silver to bronze will occur when the loose aluminum has been sufficiently removed. When the surface can be wiped or touched and no aluminum dust remains, the surface is sufficiently prepared to accept the Silicone Roof Coating System.

System Specifications

100% SILICONE ROOF COATING SYSTEM FOR CONCRETE DECKS

Oct 2024

- H. If the existing deck surface has been coated with asphalt emulsion, the roof is not acceptable for direct application of the Silicone Roof Coating System. A layer of polyester fabric must be adhered (floated) to the existing roof surface prior to the application of the primer or the silicone coatings. Apply a coat of emulsion at the rate of 3 gal/100 sf. Immediately lay the polyester fabric into the wet emulsion. Only apply enough pressure to the polyester to make positive contact with the emulsion. Do not try to fully embed the fabric into the emulsion. Allow the emulsion to dry. Apply the primer or coating at the recommended rates listed in section 1.10 Table 1.
- I. The existing deck must be returned to a structurally sound, watertight condition prior to installation of the Silicone Roof Coating System.

3.3 Surface Preparation

- A. Mechanically remove all loose coatings and/or patching material as is possible. Repairs must be made to the substrate where loose patching material is removed using like materials.
- B. Cracks, Control Joints and Expansion Joints
 1. Cracks greater than 1/8" shall be ground out to a depth of 1/2", and Mule-Hide JTS-1 Joint & Termination Sealant installed prior to coating application.
 2. Control joints shall be inspected and if damaged or deteriorated the joints shall be raked and new joints installed using backer rod and Mule-Hide JTS-1 Joint & Termination Sealant.
 3. Expansion joints shall be inspected and if damaged or deteriorated shall be repaired or replaced using appropriately sized backer rod and Mule-Hide JTS-1 Joint & Termination Sealant.
- C. Spalled or loose concrete must be removed and properly repaired returning the substrate to a sound condition.
- D. The roof surface shall be cleaned with Mule-Hide 115 Cleaner in accordance with Mule-Hide's most current Product Data Sheet. Do not dilute the 115 Cleaner. Apply direct to the roof with a mop, pump sprayer or other suitable low-pressure sprayer at a rate of .25 to .5 gallon per 100 square feet. It should be applied to the roof surface in sufficient quantity to wet the surface for a minimum of 15 minutes without drying.
- E. Apply direct to the concrete with a mop, pump sprayer or other suitable low-pressure sprayer at a rate of 1 gallon per 100 square feet. Avoid contact with painted surfaces or vinyl siding. Allow wet contact with the concrete surface for a minimum of 15 minutes. Areas that are heavily contaminated or working in hotter temperatures may require an increased application rate from 1 to 2 gallons per 100 square feet. Rewet the concrete with additional cleaner if needed. Agitate the surface with stiff bristle broom or orbital scrubber. Heavily contaminated areas may require multiple cleanings with scrubbing to obtain a clean surface.
- F. Rinse the deck surface with clean water and a minimum 2,000 psi power washer until no 115 Cleaner residue remains. Allow roof to dry completely prior to system installation. Spot check the dried concrete with a clean rag by wiping the surface of the concrete to determine if any residue remains. If the cloth shows signs of residue (dirt or chalk), then repeat the rinsing of the concrete deck. A second cleaning application may be required.
- G. Check local building ordinances for acceptable disposal of the rinse water. Many areas do not permit discharge into sewer systems or water containment areas. Compliance with local building codes and ordinances is the sole responsibility of the contractor.
- H. Allow 48 hours of dry conditions before coating.
- I. If priming deck surfaces, apply 1 coat of primer at the recommended application rate (see section 1.10 Table 1). Allow a minimum of 8 hours drying time prior to application of the 100% Silicone Roof Coating. Lower temperatures or higher humidity may require longer drying times.

3.4 Application

- A. All prep work must be done prior to coating the deck surface with the 100% Silicone Roof Coating.
- B. Cracks, Control Joints and Expansion Joints
 1. All cracks or joints must be treated with JTS-1 Joint & Termination Sealant. The overlap on both sides of the joint must be a minimum of 3-1/2 inches.
 2. Cracks 1/8" wide or less must first be filled with the JTS-1 Joint & Termination Sealant and allowed to dry until the next day (minimum of 12 hours) prior to applying the 100% Silicone Roof Coating.
 3. Cracks greater than 1/8" wide shall be ground out a minimum of 1/2" deep. The crack is then filled with JTS-1 Joint & Termination Sealant and allowed to dry until the next day (minimum of 12 hours) prior to stripping the crack with 100% Silicone Roof Coating and reinforcing fabric.
 4. Control joints shall have existing sealant removed. If needed, new backer rod shall be installed and JTS-1 Joint & Termination Sealant shall be used to fill the joint. Allow the sealant to dry until the next day (minimum of 12 hours) prior to stripping the control joint with 100% Silicone Roof Coating and reinforcing fabric.
 5. When stripping-in cracks and control joints, use a minimum 6" wide strip of the Tietex fabric embedded in 100% Silicone Coating centered over the crack/joint.
 6. Apply the 100% Silicone Roof Coating at 1 gallon per 100 square feet and immediately embed the Tietex fabric. Dry brush the fabric smooth. Apply an additional coat of 100% Silicone Roof Coating over the fabric at

System Specifications

100% SILICONE ROOF COATING SYSTEM FOR CONCRETE DECKS

Oct 2024

an application rate of 1 gallon per 100 square feet to fully encapsulate it. Allow to dry until the next day (minimum of 12 hours) prior to applying the 100% Silicone Roof Coating to the concrete deck.

C. Flashings, Curbs and Penetrations

1. Corners of curbs and parapets are coated with 100% Silicone Sealant at a rate of 1/8th of an inch thick (125 wet mils). Apply with a brush or trowel 4" wide (2" out from the corner on each side) and 1/8" to 1/4" thick tapering all edges. Allow to dry until the next day (minimum of 12 hours) prior to applying the 100% Silicone Roof Coating.
2. Curbs flashed with Mod Bit Cap Sheet shall have all seams/edges of flashings sealed with the 100% Silicone Sealant. After primer has dried, Sealant is applied 4" wide the entire length of each seam with a 4" brush, applied approximately 1/8" thick and tapered on the edges.
3. Scuppers are flashed using 100% Silicone Roof Sealant installed a minimum of 2" into the throat of the scupper, 3" minimum onto the wall or deck surrounding the scupper opening and approximately 1/8" thick.
4. Pipes are flashed using 100% Silicone Roof Sealant. If priming, allow primer to dry a minimum of 6 hours prior to application of the 100% Silicone Roof Sealant.
 - a. If the pipe flashings are in sound condition, 100% Silicone Sealant may be applied with a brush or trowel approximately 1/8" thick around the pipe base extending from the base of the pipe out approximately 3". The sealant shall also be applied vertically a minimum 8" (where possible) encapsulating the existing flashing to the point of termination.
5. Sealant pockets are flashed similar to pipes. The entire top of the pocket and penetrations (minimum 1" onto the penetration) are coated with 100% Silicone Roof Coating.
6. Sealant pockets in sound condition may be coated with the 100% Silicone Sealant applied with a brush or trowel 1/8" to 1/4" thick fully encapsulating the sealant pocket. Sealant should extend out from the base of the pocket a minimum of 3" on all sides with edges tapered to provide a smooth transition for the 100% Silicone Roof Coating.
7. Drains shall have a bead of 100% Silicone Sealant applied and feathered at the rear of the drain ring. Installation of the 100% Silicone Roof Coating shall be installed onto the feathered sealant.
8. JTS-1 Joint & Termination Sealant or Seal-Fast Liqui-Flash are acceptable substitutes for 100% Silicone Roof Sealant

D. Waterways, Valleys, and Areas Which Retain Water

1. Areas identified, after being primed as necessary, should be treated with an additional 1.0 gallon per 100 sf of 100% Silicone Roof Coating beyond the recommended application rate required for the specified warranty duration.

E. Silicone Roof Coating Application

1. Make sure all roof surfaces to receive the roof coating, are clean, free of any contamination or debris and are dry. Make sure all prep work is completed and dry prior to starting coating of the roof surface.
2. Thoroughly stir all containers of 100% Silicone Roof Coating prior to application. Do not thin this product. This product dries through absorption of moisture from the air. Avoid entraining air when mixing. Do not mix at high speeds. Dry time will be faster in humid conditions and on substrates that hold moisture such as concrete. Do not apply this product over damp or wet surfaces.
3. Open and partially full containers will skin over quickly. If this occurs, remove skin and continue using the remaining product. Mule-Hide recommends applying the 100% Silicone Roof Coating in one coat either by spraying or rolling.
4. Apply 100% Silicone Roof Coating at the application rate as determined by the warranty requirements. See Section 1.10 Warranties for application rates. Material is fast drying. Do not distribute excessive amounts onto the roof surface prior to rolling. Do not over roll as a textured finish will result. Allow coating to dry.
5. Do not over roll as a textured finish will result. Allow coating to dry. Typical drying time in 60° - 70°F temperatures is 2 to 4 hours depending on the thickness of the application.
6. If spraying, use a multi-pass technique to obtain even results. Protect unintended surfaces from overspray. It is not recommended to use a spray application if any wind is occurring.
7. If using a notched squeegee: Pour out product and spread with a 3/16" notched squeegee and immediately back roll for a smooth even finish.
8. Use a wet film thickness gauge during installation to confirm application rates.
9. See Section 1.10 Warranties for additional information on wet/dry film thickness requirements for the various warranties available from Mule-Hide.

E. Walkway Areas

1. Walkways may be constructed over newly installed silicone roof coatings with the use of the Mule-Hide Walkway granules and additional silicone coating.
2. Create outlines for the walkways by taping these areas off with masking or painters' tape.
3. Apply a fresh coat of 100% Silicone Roof Coating at a rate of 2 gal/sq (32 wet mils, 31 dry mils).
4. As soon as the silicone is applied immediately broadcast the granules into the wet coating at a minimum rate of 15 lbs. per 100 square feet. Make sure the granules completely cover the new coating.

System Specifications

100% SILICONE ROOF COATING SYSTEM FOR CONCRETE DECKS

Oct 2024

5. As soon as the granules are broadcast, remove the tape. Do not wait for the silicone to dry.
6. Do not let the silicone skin over before applying the granules as the granules will not adhere to the silicone. The silicone must be wet.
7. Allow the coating to dry until the next day. Once dry, vacuum the loose granules to prevent the excess from going into drains or gutters.
8. Over time, walkway surfaces may wear, but can easily be repaired or resurfaced by applying additional 100% Silicone Roof Coating and new granules.

Note: Walkways are maintenance items not covered by Mule-Hide warranties. Additional coating and granules and their application are the responsibility of the building owner.

3.5 Protection

Always follow OSHA guidelines for proper safety clothing and equipment when spraying products.

3.6 Clean-Up

Remove all containers, equipment, and debris from the rooftop and project site upon project completion. Refer to each individual Product Data Sheet for clean-up of each individual product.

Note: When estimating materials necessary to complete a Silicone Roof Coating System it is the Contractor's responsibility to include material calculations for waste.

END OF SECTION